

ADVA® 360

High-range water-reducing admixture

ASTM C494 Type A and F, and ASTM C1017 Type I

Product Description



ADVA® 360 is a high efficiency polycarboxylate-based super-plasticizer. ADVA 360 has been formulated to impart extreme workability without segregation to concrete, and to achieve high early compressive strength. ADVA 360 is intended for the production of Self-Consolidating Concrete (SCC) in ready-mix applications. ADVA 360 is formulated to comply with ASTM C494 as a Type A and F, and ASTM C1017 Type I admixture.

ADVA 360 is supplied as a ready-to-use brown liquid. One gallon weighs approximately 8.90 lbs (one liter weighs approximately 1.07 kg). ADVA 360 contains no intentionally added chlorides.

Uses

ADVA 360 is recommended for use in the production of conventional and SCC. ADVA 360 is a component of Grace's Self-Consolidating Concrete System.

Conventional Concrete Applications of ADVA 360:

- Can produce concrete with extremely high levels of workability without segregation.
- May be used to produce concrete with very low water/cement ratios while maintaining normal levels of workability.
- Ideal for use in applications where concrete needs to achieve high early strength along with high levels of workability.
- Provides superior concrete surface finish characteristics with reduced bugholing.

Self-Consolidating Concrete Applications:

SCC produced with ADVA 360 has unique advantages over conventional flowing concrete.

- Self placement — vibration can be eliminated because SCC is highly flowable and will change shape under its own weight to self level and self consolidate within formwork.
- No segregation — SCC is a flowable yet highly cohesive material that will not segregate, and has significantly reduced bleeding.
- No blocking — SCC can pass freely through narrow openings and congested reinforcement without aggregate “blocking” behind obstructions that stop the flow of concrete.

Product Advantages

- Imparts excellent stability to high flow concrete
- Excellent surface finish



Addition Rates

ADVA 360 is an easy to dispense liquid admixture. Dosage rates can be adjusted to meet a wide spectrum of concrete performance requirements. Addition rates for ADVA 360 can vary with the type of application, but will normally range from 3 to 12 fl oz/100 lbs (200 to 780 mL/100 kg) of cement. Should conditions require using more than the recommended addition rate, please consult your Grace representative.

The production of SCC typically requires both the use of specialty admixtures specifically tailored for SCC as well as mix design adjustments. Therefore, for SCC applications, pre-placement testing is strongly recommended to determine the optimal admixture addition rate and appropriate mix design parameters. Factors that influence optimum addition rate include other concrete mix components, aggregate gradations, form geometry, and reinforcement configurations. V-MAR® 3 may be used with ADVA 360 to further modify the rheological properties of SCC Concrete.

Compatibility with Other Admixtures and Batch Sequencing

ADVA 360 is compatible with most Grace admixtures as long as they are added separately to the concrete mix. However, ADVA products are not recommended for use in concrete containing naphthalene-based admixtures including Daracem® 19 and Daracem 100, and melamine-based admixtures including Daracem ML 330 and

Daracem 65. In general, it is recommended that ADVA 360 be added to the concrete mix near the end of the batch sequence for optimum performance. Different sequencing may be used if local testing shows better performance. Please see Grace Technical Bulletin TB-0110, *Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations* for further recommendations. ADVA 360 should not come in contact with any other admixture before or during batching, even if diluted in mix water.

Pretesting of the concrete mix should be performed before use and as conditions and materials change in order to assure compatibility with other admixtures, and to optimize dosage rates, addition times in the batch sequencing and concrete performance. For concrete that requires air entrainment, the use of an ASTM C260 air-entraining agent (such as Daravair® or Darex® product lines) is recommended to provide suitable air void parameters for freeze-thaw resistance. Please consult your Grace representative for guidance.

Packaging & Handling

ADVA 360 is available in bulk, delivered by metered trucks, in 275 gal (1041 L) totes, and 55 gal (210 L) drums. ADVA 360 will freeze at approximately 32°F (0°C) but will return to full functionality after thawing and thorough mechanical agitation.

Dispensing Equipment

A complete line of accurate, automatic dispensing equipment is available.

www.graceconstruction.com

North American Customer Service: 1-877-4AD-MIX1 (1-877-423-6491)

ADVA, the ADVA logo, V-MAR, Daracem, Daravair and Darex are registered trademarks of W. R. Grace & Co.–Conn.

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for the users' consideration, investigation and verification, but we do not warrant the results to be obtained. Please read all statements, recommendations or suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation or suggestion is intended for any use which would infringe any patent or copyright. W. R. Grace & Co.–Conn., 62 Whittemore Avenue, Cambridge, MA 02140. In Canada, Grace Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This product may be covered by patents or patents pending.
DC-53B Printed in U.S.A. 11/07

Copyright 2007. W. R. Grace & Co.–Conn.
FA/LI/1M

GRACE