

Roofing Underlayment Grace Select Specification

Part 1 General

1.01 Summary

A. Section Includes: Grace Select self-adhering membrane as a sloped roof underlayment.

B. Related Sections:

1. Section 06100—Rough Carpentry
2. Section 07220—Roof and Deck Insulation
3. Section 07311—Asphalt Shingles
4. Section 07313—Metal Shingles
5. Section 07315—Slate Shingles
6. Section 07317—Wood Shingles and Shakes
7. Section 07320—Roof Tiles
8. Section 07610—Sheet Metal Roofing
9. Section 07620—Sheet Metal Flashing and Trim

1.02 References

A. American Society for Testing and Materials (ASTM)

1. D412 Test Methods for Rubber Properties in Tension
2. D461 Standard Test Methods for Felt

3. D903 Test Methods for Peel or Stripping Strength of Adhesive Bonds

4. D3767 Standard Practice for Rubber—Measurement of Dimensions

5. E96 Test Methods for Water Vapor Transmission of Materials

1.03 Submittals

A. Manufacturer's product data sheet and product sample.

1.04 Quality Assurance

A. Manufacturer Qualifications: Self-adhesive membrane roofing underlayment shall be manufactured and marketed by W. R. Grace & Co.—Conn., Grace Construction Products, Cambridge, MA or a firm with a minimum of 25 years experience in the production and sales of self-adhered membrane roofing underlayments.

1.06 Delivery, Storage and Handling

A. The membrane and accessory products must be handled properly. Read all product labels and Material Safety Data Sheets (MSDSs) for proper handling and disposal. Deliver all materials in manufacturer's unopened packages and store all materials under cover. Do not double stack palletized material.

Part 2 Products

2.02 Manufacturers and Products

- A. Acceptable Products and Manufacturers:
Grace Select manufactured by W. R. Grace & Co.—Conn., Grace Construction Products, Cambridge, MA.

2.03 Materials

- A. Grace Select is a cold-applied, self-adhering membrane composed of a high density, cross laminated polyethylene film coated

on one side with a layer of rubberized asphalt adhesive. An embossed, slip resistant surface is provided on the polyethylene. Grace Select is interwound with a disposable silicone-coated release sheet. Membrane shall conform to the physical properties as listed in the chart below:

2.04 Accessories

- A. Accessory Products: Perm-A-Barrier® WB Primer.

Property	Value	Test Method
Color	Gray-black	
Thickness, membrane	25 mil (0.64 mm)	ASTM D3767 method A
Tensile strength, membrane	250 psi (1720 kN/m ²)	ASTM D412 (Die C modified)
Elongation, membrane	250%	ASTM D412 (Die C modified)
Adhesion to plywood	3.0 lbs/in. width (525 N/m)	ASTM D903
Permeance (max)	0.05 perms (2.9 ng/m ² s Pa)	ASTM E96
Material weight installed (max)	0.14 lb/ft ² (0.7 kg/m ²)	ASTM D461

Part 3 Execution

3.02 Preparation

- A. Install the membrane directly on a clean, dry, continuous structural deck. Some suitable deck materials include plywood, wood composition, wood plank, metal, concrete, or gypsum sheathing. Remove dust, dirt, loose nails, and old roofing materials. Protrusions from the deck area must be removed. Decks shall have no voids, damaged, or unsupported areas. Repair deck areas before installing the membrane.
- B. Prime concrete, masonry surfaces and DensDeck® with Perm-A-Barrier WB Primer at a rate of 250–350 ft²/gal (6–8 m²/L).

Prime wood composition and gypsum sheathing with Perm-A-Barrier WB Primer if adhesion is found to be marginal. (Refer to Technical Letter 12, *Use on Oriented Strand Board (OSB) Roof Sheathing.*) Apply at same rate.

- C. Priming is not required for other suitable surfaces provided that they are clean and dry.

3.03 Installation

- A. Install in strict accordance with manufacturer's printed application procedures, precautions, and limitations.

www.graceathome.com
www.graceconstruction.com

For technical assistance call toll free at 866-333-3SBM (3726)

Perm-A-Barrier is a registered trademark of W. R. Grace & Co.—Conn.
DensDeck is a registered trademark of Georgia-Pacific Corporation.

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for the users' consideration, investigation and verification, but we do not warrant the results to be obtained. Please read all statements, recommendations or suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation or suggestion is intended for any use which would infringe any patent or copyright. W. R. Grace & Co.—Conn., 62 Whittemore Avenue, Cambridge, MA 02140. In Canada, Grace Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This product may be covered by patents or patents pending.
UL-063D Printed in U.S.A. 3/07

Copyright 2007. W. R. Grace & Co.—Conn.
FA/LI/1M

GRACE